

Influence of dimensionality on superconductivity in carbon nanotubes

S. Bellucci¹, M. Cini^{1,2}, P. Onorato^{1,3} and E. Perfetto⁴

¹INFN, Laboratori Nazionali di Frascati, P.O. Box 13, 00044 Frascati, Italy

²Dipartimento di Fisica, Università di Roma Tor Vergata,
Via della Ricerca Scientifica 1 00133, Roma, Italy

³Department of Physics "A. Volta", University of Pavia, Via Bassi 6, I-27100 Pavia, Italy

⁴Consorzio Nazionale Interuniversitario per Le Scienze Fisiche della Materia,
Università di Roma Tor Vergata, Via della Ricerca Scientifica 1 00133, Roma, Italy

(Dated: February 6, 2008)

We investigate the electronic instabilities in carbon nanotubes (CNs), looking for the break-down of the one dimensional Luttinger liquid regime due to the strong screening of the long-range part of the Coulomb repulsion. We show that such a breakdown is realized both in ultra-small single wall CNs and multi wall CNs, while a purely electronic mechanism could explain the superconductivity (SC) observed recently in ultra-small (diameter $\sim 0.4\text{nm}$) single wall CNs ($T_c \sim 15^\circ\text{K}$) and entirely end-bonded multi-walled ones ($T_c \sim 12^\circ\text{K}$). We show that both the doping and the screening of long-range part of the electron-electron repulsion, needed to allow the SC phase, are related to the intrinsically 3D nature of the environment where the CNs operate.

Introduction – The recent progresses in nanotechnology allowed for a detailed study of the transport properties of 1D electron systems. The discovery of carbon nanotubes (CNs) in 1991[1], as a by-product of carbon fullerene production, opened a new field of research in mesoscopic physics[2] especially because of their potential application to nanoelectronic devices. It is known that two types of CNs, i.e. single wall carbon nanotubes (SWNTs) and multi wall carbon nanotubes (MWNTs) (see Fig.1), exist and are reported to display different electronic properties depending on their diameter and on the helicity of the carbon rings around the tubule[3]. Because of their sizes CNs usually behave as ideal one dimensional (1D) electronic systems and there have been many experiments showing the existence of superconducting (SC) correlations in these devices at low temperatures.

The SC behaviour in low dimensional systems is a quite interesting question since 40 years ago Mermin and Wagner[4] proved a famous theorem stating that it is

impossible for abrupt phase transitions with long-range order to occur in 1- or 2-D systems at finite temperature. Thus CNs are among the best candidates for investigating the possibility of (quasi)1D superconductivity. In general CNs do not show superconducting properties but some recent experiments found that ultra-small single wall carbon nanotubes[5] and entirely end-bonded multi-walled ones[6] can superconduct. Clear evidence of superconductivity was also found in CNs suspended between superconducting contacts, showing the so-called proximity effect[7, 8] while genuine superconducting transitions below 1°K have been observed in thick ropes of nanotubes suspended between normal and highly transparent electrodes[9].

Here we mainly discuss the phenomenology concerning the experiments of ref.[5] and ref.[6]. In the first experiment[5], ultra-small-diameter single wall nanotubes (USCN) have been produced inside the channels of a zeolite matrix (with inner diameter of $\sim 0.73\text{nm}$). The nanotube diameter $d = 4.2 \pm 0.2\text{\AA}$ is closer to the value calculated for a (3,3) CN geometry, although the presence of (5,0) nanotubes cannot be discarded[10]. These CNs have many unusual properties, such as superconductivity, leading to a transition temperature $T_c \approx 15^\circ\text{K}$ [5], much higher than that observed in bundles of larger diameter tubes [11].

In a recent letter[6] it was reported that there is a superconducting phase competing with the Luttinger liquid (LL) phase and even overcome it in entirely end-bonded MWNTs with a transition temperature T_c as high as 12°K . The lengths of the MWNTs were $L \sim 0.6\mu\text{m}$ while the high-resolution cross-sectional TEM images showed a MWNT with an outer diameter of $2R_o = 7.4\text{nm}$, and inner diameter of $2R_i < 2\text{nm}$ ($R < 1\text{nm}$). There was also found that the emergence of this superconductivity is highly sensitive to the junction structures of the Au electrode/MWNTs. T_c depends on the numbers of




FIG. 1: A SWNT is a rolled up sheet of graphite just nanometres in diameter and length up to some microns, while a MWNT is made by several concentrically arranged graphene sheets with a radius of some nanometers.

electrically activated shells; to enhance superconductivity the Au electrodes must be in contact with the tips of all the shells; in contrast, the conventional "bulk junction" contacts touch only the outermost shell of a tube. Below T_c the LL states are suppressed and an SC behaviour can appear while for $T > T_c$ a conventional LL behaviour was observed.

In this paper we investigate theoretically this phenomenology by focusing on the central role which the screening of the long-range part of the Coulomb repulsion plays. This screening has to be generally related to the environment (intra- and inter-shell screening in the MWNTs or screening by the zeolite matrix for the USCNs) and has an intrinsic three dimensional nature. Thus our aim is to show that the interplay between the 1D typical character of the CNs and the 3D nature of the environment allows the SC phase.

In order to pursue our aim we discuss the possibility that a superconducting behaviour can arise in these CNs by a purely electronic mechanism, i.e. neglecting the contribution of phonons. We do that by a comparison between two different approaches, one based on the Luttinger model the other one, which emphasizes the role of the lattice and short range interaction, developed starting from the Hubbard Hamiltonian.

Transport in 1D electron systems – Electronic correlations have been predicted to dominate the characteristic features in quasi 1D interacting electron systems, leading to the breakdown of the conventional Fermi liquid picture. In fact Landau quasiparticles are unstable in 1D and the low-energy excitations take the form of plasmons (collective electron-hole pair modes). Thus the 1D character of the system leads to a strong correlation among electrons, inducing of the so-called Luttinger liquid (LL)[12]. The LL state has two main features:

- i) the power-law dependence of physical quantities, such as the density of states (DOS), as a function of energy or temperature;
- ii) the spin-charge separation: an additional electron in the LL decays into decoupled spin and charge wave packets, with different velocities for charge and spin.

Characteristic experimental signatures support the assumed LL behaviour of CNs[13, 14, 15], where the temperature dependence of the resistance above a crossover temperature T_c was measured[16]. In fact the power-law dependence of physical observables follows from the behavior of the DOS as a function of the energy. For example, the tunneling conductance G in a small bias experiment[17] follows a power law,

$$G = dI/dV \propto T^\alpha \quad (1)$$

for $eV_b \ll k_B T$, where V_b is the bias voltage, T is the temperature and k_B is Boltzmann's constant. The critical exponent α assumes different values for an electrode-

bulk junction (α_{bulk}) and for an electrode-end junction (α_{end}), as reported for MWNTs in Ref.18.

The theoretical analysis start from the model of the CN where the electrons have linear dispersion relation around each of the two Fermi points at $(\pm K_F, 0)$ ($K_F = 4\pi/3a$, and $a = 2.46\text{\AA}$ is the lattice constant). These branches are highly linear with Fermi velocity $v_F \approx 8 \times 10^5$ m/s. The linear dispersion relation holds for energy scales $E < D$, with the bandwidth cutoff scale $D \approx \hbar v_F/R$ for tube radius R .

For what concerns the interaction we distinguish some processes associated with the Fermi points $\pm K_F$, (a) the *forward scattering* (g_2 with small transferred momentum $q \sim q_c = 2\pi/L$ which can be assumed as the natural infrared cut-off, depending on the longitudinal length L of the CN) (b) the *backscattering* (g_1 with large transferred momentum i.e. $q \sim 2K_F$), (c) an additional *Umklapp* process which is relevant at half-filling and in our case we neglect, since the sample is assumed to be doped (d) an additional *forward scattering* term (f) which measures the difference between intra- and inter-sublattice interactions; this term is due to the hard core of the Coulomb interaction.i.e. it follows from the unscreened short range component of the interaction. f corresponds to[12] $\delta V_p = U_{++} - U_{+-}$, where $U_{p,p'}$ is the interaction between electrons belonging to different sublattices (p, p'), and it is strongly suppressed at a distance much larger than $\ell \sim 0.3nm$ [19]. In the same way, the only non-vanishing contribution to g_1 comes from $|x - x'| \leq a$, because of rapidly oscillating contributions[12]. Thus we can assume g_2 as the only relevant long range component of the interaction. Moreover notice that the CN's dimensions play a central role in determining the strength of the different terms of the interaction. The radius R and the length L yield two natural cutoffs, $\approx \frac{2\pi}{R}$ and q_c while we can classify the physical quantity according their dependence on the radius. Thus we have a long range coupling, $g_2 = \hat{V}_0(q_c)$ weakly dependent on the radius, and two strong dependent interaction couplings, $g_1 = \hat{V}_0(2K_F)$ and f which scale as $1/R$ [12].

After introducing the values of the couplings the effective field theory can be solved in practically exact way as was done in ref.[12] and the bulk critical exponent has the form[20, 21, 22]

$$\alpha_{bulk} = \frac{1}{4} \left(g + \frac{1}{g} - 2 \right), \quad (2)$$

where g depends just on the Forward scattering as

$$\sqrt{1 + \frac{g_2}{(2\pi v_F)}} = \frac{1}{g}. \quad (3)$$

It follows that usually the short range terms of the interaction can be neglected. However it was predicted[12]

that the effects of g_1 and f can be dominant at low temperatures (T below the crossover temperatures, $g_1 \rightarrow kT_b = De^{-\frac{2\pi v_F}{g_1}}$ and $f \rightarrow kT_f = De^{-\frac{2\pi v_F}{f}} \lesssim kT_b$) where the Luttinger liquid breaks down and a (quasi-) long-range order phase appears. For long-ranged interactions (which is the case of CNs in typical conditions), we have $T_f \sim T_b$, while for short-ranged interactions it results $T_f < T_b$. In the latter case a superconducting instability is predicted at $T \sim T_f$ if the Luttinger liquid parameter g is larger than $1/2$.

Breakdown of the Luttinger Liquid – The above discussion shows that a pure electronic mechanism which gives superconductivity according the LL theory needs a screening of the forward scattering, g_2 (long range effect $g > 0.5$), an increase of the backward scattering, g_1 (short range effect T_b) and aid from the f scattering (high value of the corresponding temperature, T_f).

In typical isolated CNs of $R \gtrsim 1nm$ no SC behaviour was observed. This is in line with the above discussion, since g_1 and f are small compared to g_2 and the estimated transition temperature $T_f \sim T_b \sim 1mK$, is very low indeed. In this paper we argue about the drastic effects that one can achieve 1) by the interaction with other tubes and/or a matrix 2) by an ultra-small CN radius 3) by doping. The interactions with the surroundings can provide an effective screening of the long range component of the interaction and strongly enhance T_c . This is an interplay between 3D effects and the quasi 1D behaviour that can allow a SC transition; further 3D effects will be pointed out below for the end bonded MWNTs. The ultra-small radius contributes to enhance the short-range interaction. Although at first sight a stronger g_1 might seem to make pairing more efficient, in fact the converse is found to be true both in the LL approach and in the Hubbard model (see below). The effects of doping will also be discussed below.

In fact in the experimental samples of Ref.5 the CNs are arranged in large arrays with triangular geometry (with intertube distance $d \approx 1$ nm), behaving as a genuine 3D system concerning the screening properties. The presence of many CNs inside the zeolite matrix provides a large reduction of g_2 (by a factor $\approx 10^{-2}$), while the short range components have to remain almost unchanged. This allows for the occurrence of a sizable superconducting instability within the Luttinger liquid approach.

The SC transition in end-bonded MWNTs can be also explained as an effect of the interplay between a 3D and a 1D behaviour. In fact the power-law of the conductance observed for $T > 12^\circ K$ in the MWNTs of ref.[6] is consistent with the Luttinger liquid character of the normal state. Therefore the observed sharp breakdown of the power-law at $12^\circ K$ is an indication that an approach based on the superconducting instability of the Luttinger




FIG. 2: As already pointed out in Refs.23 and 24, the intra-tube Coulomb repulsion at small momentum transfer (i.e. in the forward scattering channel) is efficiently screened by the presence of electronic currents in neighboring nanotubes.

liquid is well posed.

The experimental results are consistent with the idea that only the outermost shell became electrically active in the Au-bulk junction (see Fig.3). In this case the conducting channel is not efficiently screened and retains a strong 1D character. The entire end-bonding of MWNTs made all the shells electrically active, while only some of the shells were electrically active in the partial Au-end junctions. Therefore, when the electrical contacts touch the top of all the shells (as in the case of the entirely end-bonded MWNTs), the activation of the internal shells gives a large dielectric effect, due to intra- and inter-shell screening, and at the same time it provides an incipient 3D character, which is crucial for establishing the superconducting coherence[25].

Thus we hypothesized that all contacted shells can transport the normal current as resistors in parallel connection. In the normal (Luttinger) state, a current of electrons flows in each shell while the conductance G is mainly given by the outermost shells, because the outermost shells have the smallest resistance. When the temperature decreases below T_c the superconductivity can be favored in the inner shells of the MWNT because the short range interactions are enhanced when the radius decreases. The long range term of the interaction, g_2 , in the end-bonded MWNTs is screened by the electronic currents located in the surrounding shells. Notice that also in this case the screening of g_2 is essentially due to the 3D nature of the MWNTs. An analogous discussion could be extended to the ropes of CNs analyzed in ref.[9].

Beyond the Luttinger Model – The above discussion provides a consistent explanation of the presence of a phase quite different from the normal (LL) one. We could also predict the crossover temperatures as reported above by using the results of ref.[12]. In this way we obtain values of T_c that are compatible with the experimental findings but are quite inaccurate. In order to improve our predictions we develop a different approach based on the Hubbard model which emphasizes the role of the lattice




FIG. 3: Electrical contacts in the systems of ref.[6] made of Au are bonded to the tubes so they touch the top of all the shells while conventional "bulk junction" contacts, in contrast, touch only the outermost shell of a tube and along its length. In usual conditions, transport measurements carried out in MWNTs reflect the electronic properties of the outer shell, which the electrodes are attached to. On the other hand, in entirely end-bonded samples the inner shells are electrically active, with relevant consequences. In particular the innermost one is able to support the transport of Cooper pairs below a temperature consistent with the measured one.

and short range interaction.

A similar analysis was developed in ref.[26] where the superconductivity in CNs was investigated with the renormalization group technique. By introducing the parameter calculated for the CNs analyzed here in the model of ref.[26] we find that a SC phase is supported just in the presence of a slight doping. Unfortunately also in this approach the estimate of T_c is quite inaccurate. A Hubbard like approach which gives a prediction about the critical temperature was proposed in ref.[19]. It is a pure electronic mechanism which leads to superconducting pairing starting from the Hubbard model on the wrapped honeycomb lattice away from half filling[27]. In this theory the ultra-small radius CN are favored for two reasons: first, the Hubbard on-site repulsion U is larger for smaller radius, and the pairing energy Δ is thereby enhanced, as we already recalled; second, at fixed U , one finds that Δ increases with decreasing radius. By using the BCS formula $\Delta = 1.76kT_c$ for the mean field transition temperature for the Ultra Small CNs of ref.[5] one estimates $T_c \approx 7 \div 70^\circ K$ which is compatible with the measured one. We observe that the lower bound $T_c \sim 7K$ takes into account that Δ may vary of about one order of magnitude away from optimal doping. Although the theory of ref.[19] has not yet been extended to the MWNT

geometry, we may expect that the inter-shell hopping should slightly enhance Δ compared to the single-shell case. Thus, we can roughly estimate the crossover temperature for the MWNTs of ref.[6]. At optimal doping we obtain $T_c \approx 4 \div 40^\circ K$. This value is slightly lower than the one of USNTs, in qualitative agreement with the experimental findings. Also in this case the lower bound $T_c \sim 4^\circ K$ is understood in terms of possible deviation from optimal doping [28].

Discussion –Here we want to discuss the intrinsic 3D nature of the model and the most relevant effects that we have to take in account.

The Hubbard model keeps only the on-site repulsion U and can be safely used under the condition that the long range component of the e-e interaction is well screened. Such screening is due to the genuine 3D nature of the systems under study.

The presence of doping deserves a specific discussion and it has to be related to some kind of external effect.

MWNTs use to be significantly doped, what leads to the presence of a large number of subbands at the Fermi level [29]. The contribution of a large number of modes at low energies has then an appreciable impact in the enhancement of observables like the DOS while the activation of several channels is also responsible of the g_2 screening. This topic was investigated in refs.[21, 22] where the effect of doping in the suppression of tunneling observed in MWNTs was studied. There was shown how the doping is related to disappearance of the typical 1D behaviour also by modifying the effective dimensionality of the system. The doping induced crossover from a 1D to a 3D behaviour is analogous to the transition from the LL to SC phase.

For what concerns the doping in the SWNTs of ref[5] the presence of the 3D environment, surrounding matrix or nearest CNs, can be assumed as the main cause of the doping. Despite the differences, the effects of the doping (screening, dimensional crossover) are quite similar to the ones discussed in the case of MWNT.

Thus we can conclude that the doping not only plays a central role in the SC instability in the Hubbard model, but contributes to the breakdown of the strictly 1D behaviour by adding several 1D conducting channels at the Fermi level and supporting the screening of the long range interaction.

S.B. and P.O. acknowledge partial financial support from the grant 2006 PRIN Sistemi Quantistici Macroscopici-Aspetti Fondamentali ed Applicazioni di strutture Josephson Non Convenzionali.

[1] S. Iijima, Nature **354**, 56 (1991).

[2] P.L. McEuen, Nature **393**, 15 (1998).

- [3] N. Hamada, S. I. Sawada, and A. Oshiyama, Phys. Rev. Lett. **68**, 1579 (1992); R. Saito *et al.*, Appl. Phys. Lett. **60**, 2204 (1992).
- [4] N.D. Mermin and H. Wagner, Phys. Rev. Letters **17**, 1133 (1966).
- [5] Z. Tang *et al.*, Science **292**, 2462 (2001).
- [6] I. Takesue *et al.*, Phys. Rev. Lett. **96**, 057001 (2006).
- [7] A. Yu. Kasumov *et al.*, Science **284**, 1508 (1999).
- [8] A. F. Morpurgo *et al.*, Science **286**, 263 (1999).
- [9] M. Kociak *et al.*, Phys. Rev. Lett. **86**, 2416 (2001). A. Kasumov *et al.*, Phys. Rev. B **68**, 214521 (2003).
- [10] H. J. Liu and C. T. Chan, Phys. Rev. B **66**, 115416 (2002).
- [11] M. Kociak, *et al.*, Phys. Rev. Lett. **86**, 2416 (2001).
- [12] R. Egger, and A. O. Gogolin, Phys. Rev. Lett. **79**, 5082 (1997); R. Egger, and A. O. Gogolin, Eur. Phys. J. B **3**, 281 (1998).
- [13] Z. Yao, H. W. Postma, L. Balents, and C. Dekker, Nature London **402**, 273 (1999).
- [14] C. Kane, L. Balents, and M. P. A. Fisher, Phys. Rev. Lett. **79**, 5086 (1997).
- [15] M. Bockrath, D. H. Cobden, J. Lu, A. G. Rinzler, R. E. Smalley, L. Balents, and P. L. McEuen, Nature **397**, 598 (1999).
- [16] J. E. Fischer, H. Dai, A. Thess, R. Lee, N. M. Hanjani, D. L. Dehaas, and R. E. Smalley, Phys. Rev. B **55**, R4921 (1997).
- [17] C. L. Kane, and M. P. A. Fisher, Phys. Rev. B **46**, 15233 (1992); C. L. Kane, and M. P. A. Fisher, Phys. Rev. Lett. **68**, 1220 (1992).
- [18] A. Bachtold *et al.*, Phys. Rev. Lett. **87**, 166801 (2001).
- [19] S. Bellucci, M. Cini, P. Onorato, and E. Perfetto, J. Phys.: Condens. Matter **18**, S2115 (2006).
- [20] S. Bellucci and J. González, Eur. Phys. J. B **18**, 3 (2000); S. Bellucci, Path Integrals from peV and TeV, edited by R. Casalbuoni, *et al.*, World Scientific, Singapore, 1999, p. 363, hep-th/9810181; S. Bellucci and J. González, Phys. Rev. B **64**, 201106 (2001).
- [21] S. Bellucci, J. González and P. Onorato, Nucl. Phys. B **663** [FS], 605 (2003); S. Bellucci and P. Onorato, Ann. Phys. **321**, 934 (2006).
- [22] S. Bellucci, J. González and P. Onorato, Phys. Rev. B **69**, 085404 (2004). S. Bellucci and P. Onorato, Phys. Rev. B **71**, 075418 (2005); S. Bellucci, J. Gonzalez, and P. Onorato, Phys. Rev. Lett. **95**, 186403 (2005).
- [23] J. González, and E. Perfetto, Phys. Rev. B **72**, 205406 (2005).
- [24] J. González and E. Perfetto, Eur. Phys. J. **51**, 571 (2006).
- [25] E. Perfetto and J. González, Phys. Rev. B **74**, 201403 (2006).
- [26] Yu.A. Krotov, D.H. Lee, and S.G. Louie, Phys. Rev. Lett. **78**, 4245 (1997).
- [27] E. Perfetto, G. Stefanucci, and M. Cini Phys. Rev. B **66**, 165434 (2002).
- [28] S. Bellucci, M. Cini, P. Onorato, and E. Perfetto, Phys. Rev. B **75**, 014523 (2007)
- [29] M. Krüger, M. R. Buitelaar, T. Nussbaumer, C. Schönenberger, and L. Forró, Appl. Phys. Lett. **78**, 1291 (2001)